

## ABS Material Data Sheet

<b>Physical Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	Grade Count = 3
Melt Flow	18 - 23 g/10 min	18 - 23 g/10 min	Average = 21.3 g/10 min; Grade Count = 3
<b>Mechanical Properties</b>			
Hardness, Rockwell R	103 - 112	103 - 112	Average = 110; Grade Count = 3
Tensile Strength, Yield	42.5 - 44.8 MPa	6160 - 6500 psi	Average = 44 MPa; Grade Count = 3
Elongation at Break	23 - 25 %	23 - 25 %	Average = 24.3%; Grade Count = 3
Flexural Modulus	2.25 - 2.28 GPa	326 - 331 ksi	Average = 2.3 GPa; Grade Count = 3
Flexural Yield Strength	60.6 - 73.1 MPa	8790 - 10600 psi	Average = 68.9 MPa; Grade Count = 3
Izod Impact, Notched	2.46 - 2.94 J/cm	4.61 - 5.51 ft-lb/in	Average = 2.8 J/cm; Grade Count = 3
<b>Electrical Properties</b>			
Arc Resistance	120 sec	120 sec	Grade Count=1
Comparative Tracking Index	600 V	600 V	Grade Count=1
Hot Wire Ignition, HWI	15 sec	15 sec	Grade Count = 1
High Amp Arc Ignition, HAI	120 arcs	120 arcs	Grade Count = 1
High Voltage Arc-Tracking Rate, HVTR	25 mm/min	0.984 in/min	Grade Count = 1
<b>Thermal Properties</b>			
Maximum Service Temperature, Air	88 - 89 °C	190 - 192 °F	Average = 88.7°C; Grade Count = 3
Deflection Temperature at 1.8 MPa (264 psi)	88 - 89 °C	190 - 192 °F	Average = 88.7°C; Grade Count=3
Vicat Softening Point	100 °C	212 °F	Grade Count = 1
Flammability, UL94	HB	HB	Grade Count = 3

